

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89301397.9

(51) Int. Cl.⁴: **C 08 G 18/77**
C 08 G 18/38

(22) Date of filing: 15.02.89

(30) Priority: 17.02.88 JP 32842/88
18.02.88 JP 33871/88
18.02.88 JP 33872/88
22.02.88 JP 37515/88
22.02.88 JP 37523/88
22.02.88 JP 37525/88

(43) Date of publication of application:
23.08.89 Bulletin 89/34

(84) Designated Contracting States:
CH DE FR GB IT LI NL

(71) Applicant: **MITSUI TOATSU CHEMICALS, INCORPORATED**
2-5, 3-chome, Kasumigaseki
Chiyoda-ku Tokyo (JP)

(72) Inventor: **Nagata, Teruyuki**
154, Shiraganemachi
Omatu-shi Fukuoka-ken (JP)

Okazaki, Koju
35, Yamashitamachi
Omatu-shi Fukuoka-ken (JP)

Kajimoto, Nobuyuki
4-1413-1315, Shiomidai 1-chome Isogo-ku
Yokohama-shi Kanagawa-ken (JP)

Miura, Tohru
1612-1-26, Kosugayacho Sakae-ku
Yokohama-shi Kanagawa-ken (JP)

Kanemura, Yoshinobu
2882, Iijimacho Sakae-ku
Yokohama-shi Kanagawa-ken (JP)

Sasagawa, Katsuyoshi
1510-1-411, Shinyoshidacho Kohoku-ku
Yokohama-shi Kanagawa-ken (JP)

(74) Representative: **Stuart, Ian Alexander et al**
MEWBURN ELLIS & CO. 2/3 Cursitor Street
London EC4A 1BQ (GB)

(54) **Resin for plastics lens, and method for its preparation.**

(57) The present invention relates to resin useful in preparing plastic lenses having a high refractive index comprising reacting an aliphatic polyisocyanate compounds having at least one sulfur atom with one or more of active hydrogen compounds selected from the group consisting of a polyol, a polythiol having sulfur atoms only in a mercapto groups, and a polythiol having at least one sulfur atom other than in the mercapto groups: lenses containing the above mentioned resin; and a method for the preparation thereof characterized by adding an internal release agent to the mixture of the above-mentioned raw materials in casting lenses from the resin and lenses obtained by this method.

EP 0 329 387 A2

Description

RESIN FOR PLASTIC LENS, AND METHOD FOR ITS PREPARATION

The present invention relates to a resin useful in preparing plastic lenses having a high-refractive index, lenses containing the resin, and a method for the preparation of such lenses.

In recent years, plastic lenses are rapidly being more frequently utilized as optical elements in eyeglasses, cameras and the like, because they are lighter, more unbreakable and more dyeable than inorganic lenses.

A resin which can be prepared by the radical polymerization of diethylene glycol bis(allyl carbonate) (hereinafter referred to simply as DAC) has been used to prepare such lenses. This resin has a high impact resistance, is lightweight, and exhibits excellent dyeing properties and good workability of cutting and polishing.

However, lenses prepared from the above-mentioned resin have a lower refractive index ($n_D = 1.50$) than inorganic lenses ($n_D = 1.52$). In order to obtain equivalent optical properties to glass lenses, it is necessary to increase the central thickness, peripheral thickness and curvature of the lens and hence the lens becomes very thick. For this reason, resins having a high-refractive index are desired. Resins which have been previously used to prepare lenses having a high-refractive index include resins prepared by reacting an isocyanate compound with diethylene glycol (U.S. Patent No. 4,443,588), reacting an isocyanate compound with a hydroxyl compound containing a halogen atom such as tetrabromobisphenol A (Japanese Patent Laid-open Publication No. 164615/1983), or reacting an isocyanate compound with a hydroxyl compound containing a diphenyl sulfide skeleton (Japanese Patent Laid-open Publication No. 194401/1985).

The present inventors have previously proposed high-refractive plastic lenses comprising polyurethane resins or the like which can be prepared by reacting an isocyanate compound with a hydroxyl compound having a sulfur atom (U.S. Patent Nos. 4,680,369 and 4,780,552) or reacting an isocyanate compound with a polythiol (U.S. Patent No. 4,689,387 and Japanese Patent Laid-open Publication No. 267316/1987).

Lenses comprising previously known resins have a higher refractive index than the lenses containing DAC, however, the refractive index thereof is still insufficient. Such resins have drawbacks such as high dispersion, poor weatherability and great specific gravity, since the resins are made from compounds containing numerous halogen atoms or aromatic rings to improve the refractive index.

It has been known to add an internal releasing agent during the process for preparing such lenses to improve mold release characteristics. In such process butyl phosphate is added to DAC. However, the addition of butyl phosphate is not required, and results in impaired appearance of the molded articles. [Seiichi Mima, "Polymer Digest", 3, 39 (1984) and the like].

In molding polyurethane and S-alkyl thiocarbamic acid ester lenses, it is difficult to release the lens from the mold after polymerization. In order to solve this problem, the present inventors invented a method in which an external releasing agent is employed (Japanese Patent Laid-open Publication No. 267316/1987) and a method in which a mold made from polyolefin resin is employed (Japanese Patent Laid-open Publication No. 236818/1987).

However, these above mold release methods are still insufficient for improving mold release property in the cast polymerization because of the lens according to the present invention.

In the method in which an external releasing agent is employed, a surface treatment material for treating the inner surface of the mold is partially transferred to the surface and interior of the polymerized lenses, causing the lens surface to be uneven and turbid. The mold release treatment is required each time the mold is used. Accordingly, this method is intricate, decreases lens productivity, and thus is uneconomical.

Further, a polyolefin resin mold, is deformed at elevated temperatures, resulting in poor accuracy of the lens surfaces. Thus, the method cannot be applied in applications where high surface accuracy is required.

Preferred embodiments of the present invention may achieve one or more of the following: ameliorate the problems and disadvantages of the prior art by providing a resin having improved properties over prior art resins, a process for producing the same, and a lens containing the resin having superior properties over prior art lenses, and a process for producing the lens;

provide a resin having excellent optical properties;

provide a colorless and transparent resin having a high refractive index which is suitable for use in lenses;

provide a process for producing lenses efficiently and economically on an industrial scale;

provide plastic lenses having a high refractive index, high surface accuracy, excellent optical properties, excellent impact resistance, and which are lightweight and suitable for use in eyeglasses and cameras.

Additional objects and advantages of the invention will be set forth in part in the description which follows, and in part will be obvious from the description, or may be learned by practice of the invention. The objects and advantages of the invention may be realized and attained by means of the instrumentalities and combinations, particularly pointed out in the appended claims.

The invention provides a process for producing a resin comprising reacting (a) one or more aliphatic polyisocyanate compounds having at least one sulfur atom with (b) one or more active hydrogen compounds selected from polyol compounds, polythiol compounds having sulfur atoms only in mercapto groups, and polythiol compounds having at least one sulfur atom in addition to the sulfur atoms contained in the mercapto group(s).

The present invention also provides a process for producing a lens containing the resin of the invention

comprising forming a mixture of (a) one or more aliphatic polyisocyanate compounds having at least one sulfur atom; (b) one or more active hydrogen compounds selected from polyol compounds, polythiol compounds having sulfur atoms only in mercapto groups, and polythiol compounds having at least one sulfur atom in addition to the sulfur atom in the mercapto groups and (c) at least one internal releasing agent; pouring the mixture into a mold and polymerizing the mixture to form said lens.

A resin embodying the invention may have excellent optical properties, be colorless and of high refractive index. The plastic lenses of the invention may have high surface accuracy, excellent weatherability, exhibit excellent impact resistance and optical properties and be manufacturable extremely efficiently on an industrial scale by the use of a usual glass mold without any specific mold release treatment.

Reference will now be made in detail to the present preferred embodiments of the invention.

Exemplary aliphatic polyisocyanate compounds containing at least one sulfur atom and suitable for use in the processes of the invention include noncyclic aliphatic polyisocyanate compounds containing sulfur atom such as thiodiethyl diisocyanate, thiodipropyl diisocyanate, thiodihexyl diisocyanate, dimethylsulfine diisocyanate, dithiodimethyl diisocyanate, dithiodiethyl diisocyanate and dithiodipropyl diisocyanate; an aliphatic isocyanate containing sulfur atom and an aromatic ring such as bis[(4-isocyanatomethyl)benzene] sulfide; a cyclic aliphatic isocyanate containing sulfur atom such as 1,4-dithian-2,5-diisocyanate; and an aliphatic isocyanate containing sulfur atom and a heterocyclic ring.

Halogen-substituted compounds such as chlorine-substituted and bromine-substituted compounds of these polyisocyanates, biuret reaction products thereof, adduct reaction products of the polyisocyanates and trimethylol-propane, and dimerization and trimerization reaction products of the polyisocyanate compounds are also suitable for use in the process of the invention.

The polyisocyanate compounds may be used alone or in a mixture of two or more thereof.

Exemplary active hydrogen compounds suitable for use in the process of the invention include a polyol compound, a polythiol compound containing sulfur atoms only in mercapto groups, and a polythiol compound containing at least one sulfur atom in addition to the sulfur atom in mercapto groups.

Exemplary suitable polyol compounds include polyols such as ethylene glycol, diethylene glycol, propylene glycol, dipropylene glycol, butylene glycol, neopentyl glycol, glycerin, trimethylethane, trimethylolpropane, butanetriol, 1,2-methyl glycoside, pentaerythritol, dipentaerythritol, tripentaerythritol, sorbitol, erythritol, threitol, ribitol, arabinitol, xylitol, allitol, mannitol, dorcitol, iditol, glycol, inositol, hexanetriol, triglycerol, diglycerol, triethylene glycol, polyethylene glycol, tris(2-hydroxyethyl) isocyanurate, cyclobutanediol, cyclopentanediol, cyclohexanediol, cycloheptanediol, cyclooctanediol, cyclohexanedimethanol, hydroxypropylcyclohexanol, tricyclo(5,2,1,0^{2,6})decane dimethanol, bicyclo(4,3,0)nonanediol, dicyclohexanediol, tricyclo(5,3,1,1)dodecanediol, bicyclo(4,3,0)nonanedimethanol, tricyclo(5,3,1,1)dodecane diethanol, hydroxypropyltricyclo(5,3,1,1)dodecanol, spiro(3,4)octanediol, butyl cyclohexanediol, 1,1-bicyclohexyldenediol, cyclohexanetriol, maltitol, lactitol, dihydroxynaphthalene, trihydroxynaphthalene, tetrahydroxynaphthalene, dihydroxybenzene, benzenetriol, biphenyltetraol, pyrogallol, (hydroxynaphthyl)pyrogallol, trihydroxyphenanthrene, bisphenol A, bisphenol F, xylene glycol, di(2-hydroxyethoxy)benzene, bisphenol A-bis-(2-hydroxyethyl ether), tetrabromobisphenol A, tetrabromobisphenol A-bis(2-hydroxy ethyl ether), dibromoneopentyl glycol and epoxy resin; condensation reaction products of these polyols and organic polybasic acids such as oxalic acid, glutamic acid, adipic acid, acetic acid, propionic acid, cyclohexanecarboxylic acid, β -oxocyclohexanepropionic acid, dimer acid, phthalic acid, isophthalic acid, salicylic acid, 3-bromopropionic acid, 2-bromoglycolic acid, dicarboxycyclohexane, pyromellitic acid, butanetetracarboxylic acid and bromophthalic acid; addition reaction products of the above-mentioned polyols and alkylene oxides such as ethylene oxide and propylene oxide; and addition reaction products of alkylene polyamines and alkylene oxides such as ethylene oxide and propylene oxide.

Halogen-substituted compounds such as chlorine-substituted and bromine-substituted compounds of these above polyol compounds are also suitable for use in the process of the invention.

Exemplary polythiol compounds having sulfur atoms only in the mercapto groups suitable for use in the processes of the invention include aliphatic polythiols such as methanedithiol, 1,2-ethanedithiol, 1,1-propanedithiol, 1,2-propanedithiol, 1,3-propanedithiol, 2,2-propanedithiol, 1,6-hexanedithiol, 1,2,3-propanetrithiol, 1,1-cyclohexanedithiol, 1,2-cyclohexanedithiol, 2,2-dimethylpropane-1,3-dithiol, 3,4-dimethoxybutane-1,2-dithiol, 2-methylcyclohexane-2,3-dithiol, bicyclo(2,2,1)hepta-exo-cis-2,3-dithiol, 1,1-bis(mercaptomethyl)cyclohexane, thiomalic acid bis(2-mercaptoethyl ester), 2,3-dimercaptosuccinic acid (2-mercaptoethyl ester), 2,3-dimercapto-1-propanol(2-mercapto acetate), 2,3-dimercapto-1-propanol(3-mercapto propionate), diethylene glycol bis(2-mercapto acetate), diethylene glycol bis(3-mercapto propionate), 1,2-dimercaptopropyl methyl ether, 2,3-dimercaptopropyl methyl ether, 2,2-bis(mercaptomethyl)-1,3-propanedithiol, bis(2-mercaptoethyl) ether, ethylene glycol bis(2-mercapto acetate), ethylene glycol bis(3-mercapto propionate), trimethylolpropanebis(2-mercapto acetate), trimethylolpropane bis(3-mercapto propionate), pentaerythritoltetrakis(2-mercapto acetate) and pentaerythritoltetrakis(3-mercapto propionate), and halogen-substituted compounds such as chlorine-substituted and bromine-substituted compounds thereof; aromatic polythiols such as 1,2-dimercaptobenzene, 1,3-dimercaptobenzene, 1,4-dimercaptobenzene, 1,2-bis(mercaptomethyl)benzene, 1,3-bis(mercaptomethyl)benzene, 1,4-bis(mercaptomethyl)benzene, 1,2-bis(mercaptoethyl)benzene, 1,3-bis(mercaptoethyl)benzene, 1,4-bis(mercaptoethyl)benzene, 1,2-bis(mercaptomethyleneoxy)benzene, 1,3-bis(mercaptomethyleneoxy)benzene, 1,4-bis(mercaptomethyleneoxy)benzene, 1,2-bis(mercaptoethyleneoxy)benzene, 1,3-bis(mercaptoethyleneoxy)benzene, 1,4-bis(mercaptoethyleneoxy)benzene,

1,2,3-trimercaptobenzene, 1,2,4-trimercaptobenzene, 1,3,5-trimercaptobenzene, 1,2,3-tris(mercaptomethyl)benzene, 1,2,4-tris(mercaptomethyl)benzene, 1,3,5-tris(mercaptomethyl)benzene, 1,2,3-tris(mercaptoethyl)benzene, 1,2,4-tris(mercaptoethyl)benzene, 1,3,5-tris(mercaptoethyl)benzene, 1,2,3-tris(mercaptoethyleneoxy)benzene, 1,2,4-tris(mercaptoethyleneoxy)benzene, 1,3,5-tris(mercaptoethyleneoxy)benzene, 1,2,3-tris(mercaptoethyleneoxy)benzene, 1,2,4-tris(mercaptoethyleneoxy)benzene, 1,3,5-tris(mercaptoethyleneoxy)benzene, 1,2,3,4-tetramercaptobenzene, 1,2,3,5-tetramercaptobenzene, 1,2,4,5-tetramercaptobenzene, 1,2,3,4-tetrakis(mercaptomethyl)benzene, 1,2,3,5-tetrakis(mercaptomethyl)benzene, 1,2,4,5-tetrakis(mercaptomethyl)benzene, 1,2,3,4-tetrakis(mercaptomethyl)benzene, 1,2,3,5-tetrakis(mercaptoethyl)benzene, 1,2,4,5-tetrakis(mercaptoethyl)benzene, 1,2,3,4-tetrakis(mercaptoethyleneoxy)benzene, 1,2,3,5-tetrakis(mercaptoethyleneoxy)benzene, 1,2,4,5-tetrakis(mercaptoethyleneoxy)benzene, 1,2,3,4-tetrakis(mercaptoethyleneoxy)benzene, 1,2,3,5-tetrakis(mercaptoethyleneoxy)benzene, 1,2,4,5-tetrakis(mercaptoethyleneoxy)benzene, 2,2'-dimercaptobiphenyl, 4,4'-dimercaptobiphenyl, 4,4'-dimercaptobiphenyl, 2,5-toluenedithiol, 3,4-toluenedithiol, 1,4-naphthalenedithiol, 1,5-naphthalenedithiol, 2,6-naphthalenedithiol, 2,7-naphthalenedithiol, 2,4-dimethylbenzene-1,3-dithiol, 4,5-dimethylbenzene-1,3-dithiol, 9,10-anthracenedimethanethiol, 1,3-di(p-methoxyphenyl)propane-2,2-dithiol, 1,3-diphenylpropane-2,2-dithiol, phenylmethane-1,1-dithiol and 2,4-di(p-mercaptophenyl)pentane; halogen-substituted aromatic polythiols, for example, chlorine-substituted and bromine-substituted compounds such as 2,5-dichlorobenzene-1,3-dithiol, 1,3-di(p-chlorophenyl)propane-2,2-dithiol, 3,4,5-tribromo-1,2-dimercaptobenzene and 2,3,4,6-tetrachloro-1,5-bis(mercaptomethyl)benzene; polythiols each containing a heterocyclic ring such as 2-methylamino-4,6-dithiol-sym-triazine, 2-ethylamine-4,6-dithiol-sym-triazine, 2-amino-4,6-dithiol-sym-triazine, 2-morpholino-4,6-dithiol-sym-triazine, 2-cyclohexylamino-4,6-dithiol-sym-triazine, 2-methoxy-4,6-dithiol-sym-triazine, 2-phenoxy-4,6-dithiol-sym-triazine, 2-thiobenzeneoxy-4,6-dithiol-sym-triazine and 2-thiobutyloxy-4,6-dithiol-sym-triazine, and halogen-substituted compounds such as chlorine-substituted and bromine-substituted compounds thereof.

Exemplary polythiol compounds containing at least one sulfur atom in addition to the sulfur atom in mercapto groups include aromatic polythiols such as 1,2-bis(mercaptomethylthio)benzene, 1,3-bis(mercaptomethylthio)benzene, 1,4-bis(mercaptomethylthio)benzene, 1,2-bis(mercaptoethylthio)benzene, 1,3-bis(mercaptoethylthio)benzene, 1,4-bis(mercaptoethylthio)benzene, 1,2,3-tris(mercaptomethylthio)benzene, 1,2,4-tris(mercaptomethylthio)benzene, 1,3,5-tris(mercaptomethylthio)benzene, 1,2,3-tris(mercaptoethylthio)benzene, 1,2,4-tris(mercaptoethylthio)benzene, 1,3,5-tris(mercaptoethylthio)benzene, 1,2,3,4-tetrakis(mercaptomethylthio)benzene, 1,2,3,5-tetrakis(mercaptomethylthio)benzene, 1,2,4,5-tetrakis(mercaptomethylthio)benzene and their nucleus-alkylated compounds; aliphatic polythiols such as bis(mercaptomethyl) sulfide, bis(mercaptoethyl) sulfide, bis(mercaptopropyl) sulfide, bis(mercaptomethylthio)methane, bis(2-mercaptoethylthio)methane, bis(3-mercaptopropylthio)methane, 1,2-bis(mercaptomethylthio)ethane, 1,2-bis(mercaptoethylthio)ethane, 1,2-bis(3-mercaptopropylthio)ethane, 1,3-bis(mercaptomethylthio)propane, 1,3-bis(2-mercaptoethylthio)propane, 1,3-bis(3-mercaptopropylthio)propane, 1,2,3-tris(mercaptomethylthio)propane, 1,2,3-tris(2-mercaptoethylthio)propane, 1,2,3-tris(3-mercaptopropylthio)propane, tetrakis(mercaptomethylthiomethyl)methane, tetrakis(2-mercaptoethylthiomethyl)methane, tetrakis(3-mercaptopropylthiomethyl)methane, bis(2,3-dimercaptopropyl) sulfide, 2,5-dimercapto-1,4-dithiane, bis(mercaptomethyl) disulfide, bis(mercaptoethyl) disulfide, bis(mercaptopropyl) disulfide, and esters of these compounds and thioglycolic acid or mercaptopropionic acid, hydroxymethyl sulfide bis(2-mercapto acetate), hydroxymethyl sulfide bis(3-mercapto propionate), hydroxyethyl sulfide bis(2-mercapto acetate), hydroxyethyl sulfide bis(3-mercapto propionate), hydroxypropyl sulfide bis(2-mercapto acetate), hydroxypropyl sulfide bis(3-mercapto propionate), hydroxymethyl disulfide bis(2-mercapto acetate), hydroxymethyl disulfide bis(3-mercapto propionate), hydroxyethyl disulfide bis(2-mercapto acetate), hydroxyethyl disulfide bis(3-mercapto propionate), hydroxypropyl disulfide bis(2-mercapto acetate), hydroxypropyl disulfide bis(3-mercapto propionate), 2-mercapto ethyl ether bis(2-mercapto acetate), 2-mercapto ethyl ether bis(3-mercapto propionate), 1,4-dithian-2,5-diolbis(2-mercapto acetate), 1,4-dithian-2,5-diolbis(3-mercapto propionate), thiodiglycolic acid bis(2-mercapto ethyl ester), thiodipropionic acid bis(2-mercapto ethyl ester), 4,4-thiodibutylic acid bis(2-mercapto ethyl ester), dithiodiglycolic acid bis(2-mercapto ethyl ester), dithiodipropionic acid bis(2-mercapto ethyl ester), 4,4-dithiodibutylic acid bis(2-mercapto ethyl ester), thiodiglycolic acid bis(2,3-dimercapto propyl ester), thiodipropionic acid bis(2,3-dimercapto propyl ester), dithiodiglycolic acid bis(2,3-dimercapto propyl ester) and dithiodipropionic acid bis(2,3-dimercapto propyl ester); and heterocyclic compounds such as 3,4-thiophenedithiol, bismuthiol and 2,5-dimercapto-1,3,4-thiadiazole.

Halogen-substituted compounds such as chlorine-substituted and bromine-substituted compounds of the above polythiol compounds may also be employed. These active hydrogen compounds may be used alone or in a mixture of two or more thereof.

The molar ratio of the functional groups of the polyisocyanate compound to the functional groups of the active hydrogen compound is from about 0.5 to about 3.0, preferably from about 0.5 to about 1.5, i.e., NCO/(OH + SH).

In the plastic lens of the present invention, a urethane resin or an S-alkyl thiocarbamic acid ester resin is used as a raw material. Therefore in the plastic lens a urethane bond is present between an isocyanate group and a hydroxyl group, or an S-alkyl thiocarbamic acid ester bond is present between the isocyanate group and the mercapto group. However, the plastic lens of the present case may contain an allophanate bond, a urea

bond, a biuret bond or the like in addition to the above bond depending on the intended end use of the lens.

For example, the isocyanate group may be further reacted with the urethane bond or S-alkyl thiocarbamic acid ester bond so as to increase the crosslink density. In this case, the reaction temperature is set to 100°C or more, and the isocyanate component is used in an excess amount. Alternatively, an amine or the like may be used to utilize the urea bond or biuret bond. When the isocyanate compound is reacted with a compound other than the hydroxyl compound or mercapto compound, attention must be paid to coloring.

Various additives may be added to the raw materials to achieve particular properties for end use and lens of the invention. Exemplary suitable additives include a chain extender, a crosslinking agent, a light stabilizer, an ultraviolet absorbent, an anti-oxidant, an oil-soluble dye and a filler.

For the purpose of adjusting the reaction rate to a desired level, a known reaction catalyst may be added which can be generally used in the manufacture of the polyurethane or S-alkyl thiocarbamic acid ester.

The plastic lens of the present invention can be prepared by cast polymerization. One or more of aliphatic polyisocyanate compounds containing sulfur atom; one or more of active hydrogen compounds and at least one internal releasing agent are mixed to form a mixture; the resulting mixture is casted into a mold, and then polymerization is carried out.

Exemplary suitable internal releasing agents useful in the present invention include fluorine containing nonionic surface active agents, silicon containing nonionic surface active agents, alkyl quaternary ammonium salts, acidic phosphates, liquid paraffins, waxes, higher fatty acids and metallic salts thereof, higher fatty esters, higher fatty alcohols, bisamides, polysiloxanes and aliphatic amine ethylene oxide adducts. They can be suitably selected in view of the combination of monomers, polymerization conditions, economy and ease of handling.

The internal releasing agents may be used alone or in a mixture of two or more thereof.

The fluorine containing nonionic surface active agents and the silicon containing nonionic surface active agents, which are used as the internal releasing agents in the present invention, are compounds each having a perfluoroalkyl group or a dimethylpolysiloxane group, a hydroxyalkyl group and a phosphoric ester group. Exemplary suitable fluorine containing nonionic surface active agents commercially available include Unidain®: DS-401 and DS-403 (products of Daikin Kogyo Co., Ltd.), F-Top®: EF122A, EF126 and EF301 (products of Shinakita Chemical Co., Ltd.). An exemplary silicon containing nonionic surface active agents is a trial product Q2-120A of Dow Chemical Co..

Exemplary suitable alkyl quaternary ammonium salts useful as the internal releasing agents in the present invention include as cationic surface active agents such as alkyl quaternary ammonium salts including halogen salts, phosphates and sulfates of alkyl quaternary ammonium. Typical exemplary chlorides thereof include trimethylacetylammmonium chloride, trimethylstearylammmonium chloride, dimethylethylcetylammmonium chloride, triethyldodecylammmonium chloride, trioctylmethylammmonium chloride and diethylcyclohexyldodecylammmonium chloride.

Exemplary suitable acidic phosphate compounds for use as the internal releasing agent in the present invention include isopropyl acid phosphate, diisopropyl acid phosphate, butyl acid phosphate, dibutyl acid phosphate, octyl acid phosphate, dioctyl acid phosphate, isodecyl acid phosphate, diisodecyl acid phosphate, tridecanol acid phosphate and bis(tridecanol acid) phosphate.

Exemplary suitable metallic salts of the higher fatty acids useful as the internal releasing agents in the present invention include zinc salts, calcium salts, magnesium salts, nickel salts, copper salts and other salts of stearic acid, oleic acid, octanoic acid, lauric acid, behenic acid and ricinoleic acid such as zinc stearate, zinc oleate, zinc palmitate, zinc laurate, calcium stearate, calcium oleate, calcium palmitate, calcium laurate, magnesium stearate, magnesium oleate, magnesium laurate, magnesium palmitate, nickel stearate, nickel oleate, nickel palmitate, nickel laurate, copper stearate, copper oleate, copper laurate and copper palmitate.

Exemplary suitable higher fatty esters useful as the internal releasing agent in the present invention include esters of higher fatty acids such as stearic acid, oleic acid, octanoic acid, lauric acid and ricinoleic acid and alcohols such as ethylene glycol, dihydroxypropane, dihydroxybutane, neopentyl glycol and dihydroxyhexane.

The amount of the internal releasing agent to be used, which may be used alone or in the form of a mixture two or more thereof, is from about 0.1 to about 10,000 ppm, preferably from about 1 to about 5,000 ppm based on the total weight of a monomer mixture.

When the amount of the internal releasing agent is less than 0.1 ppm, mold release characteristics are bad; when it is in excess of 10,000 ppm, the lenses are turbid, and each lens is prematurely separated from the mold during polymerization and the surface accuracy of the lenses deteriorates.

Polymerization is carried out at from about -20°C to about 200°C, preferably from about room temperature to about 150°C, more preferably from about 50°C to about 120°C, in from 0.5 to 72 hours, depending upon the types of monomers and the mold releasing agent employed.

The polymerized lenses may be subjected to an annealing treatment, if necessary.

The plastic lenses of the present invention have high surface accuracy and excellent optical properties, are lightweight and excellent in impact resistance, and are suitable for optical element materials such as lenses of glasses and cameras.

Moreover, the plastic lenses of the present invention can be subjected to physical and chemical treatments such as surface abrasion treatment, antistatic treatment, hard coat treatment, non-reflective coat treatment, coloring treatment and dimming treatment for the prevention of reflection, enhancement of hardness, improvement of abrasion resistance and chemical resistance, prevention of turbidity, supply of fashionability,

and the like.

Now, the present invention will be further described and clarified by the following examples and comparative examples which are intended to be purely exemplary of the invention. The performance tests of the resins and lenses, specifically the tests of refractive index, Abbe's number, weatherability, mold release characteristics and appearance were carried out by the following procedure:

Refractive index and Abbe's number: Measured at 20°C by the use of a Pulfrich refractometer.

Weatherability: A resin specimen was set on a weatherometer equipped with a sunshine carbon arc lamp, and after 200 hours had elapsed, the resin specimen was taken out therefrom. Afterward, the specimen was compared in tint with the resin for lens which had not been subjected to the test. Evaluation was made by the ranking of "not changed", "slightly yellowed" and "yellowed" denoted by "O", "Δ" and "X", respectively.

Mold release characteristics: When a polymerized lense was released from a mold without resistance, the mold release characteristics denoted by "O", and when a part or all of the lense was not released therefrom, they denoted by "X", by mean of driving in a Tefron wedge between the lens and the mold.

Appearance: It was evaluated by visual observation.

Example 1

18.4 g (0.09 mol) of dithiodiethyl diisocyanate were mixed with 8.0 g (0.06 mol) of 1,2,6-hexanetriol. The resulting mixture was poured into a mold composed of a glass mold and a gasket, the temperature was raised slowly from room temperature to 120°C taking 28 hours, to complete the polymerization. The thus obtained lens was colorless and excellent in weatherability, had a refractive index n_D^{20} of 1.57, an Abbe's number v_D^{20} of 44 and a specific gravity of 1.32.

Examples 2 to 18 and Comparative Examples 1 to 3

Following the procedure of Example 1, lenses were prepared in composition ratios shown in Table 1. The results of performance tests are set forth in Table 1.

Example 19

18.4 g (0.09 mol) of dithioethyl diisocyanate, 8.0 g (0.06 mol) of 1,2,6-hexanetriol and 0.03 g of isopropyl acid phosphate were mixed. The resulting mixture was poured into a mold composed of a glass mold and a gasket, and was gradually heated from room temperature to 120°C taking 28 hours, to complete the polymerization. After the polymerization, a lens was released from the mold with ease. The thus obtained lens was colorless and had good surface accuracy. Moreover, it had a refractive index n_D^{20} of 1.57 and an Abbe's number v_D^{20} of 44.

Examples 20 to 47

Following the procedure of Example 19, lenses were prepared in composition ratios shown in Table 2. The results of performance tests are set forth in Table 2.

Comparative Examples 4 to 27

Following the procedure of Example 19 with the exception that the undermentioned mold treatments were carried out, lenses were prepared in the composition ratios shown in Table 3. The results of performance tests are set forth in Table 3.

(1) No treatment A glass mold was used without any release treatment.

(2) External release treatment External mold releasing agent YSR-6209® (product of Toshiba Silicon Co.) was applied and baked on the inner surface of a glass mold.

(3) Reuse of external release treatment The glass mold obtained by the external release treatment was once employed for the polymerization and then used again without any further treatment.

(4) Use of PP mold A polypropylene mold was prepared by injection molding and used in place of the glass mold without any surface treatment.

Other embodiments of the invention will be apparent to the skilled in the art from consideration of the specification and practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the invention being indicated by the following claims.

Table 1 (I)

	Active Hydrogen Compound	Polyisocyanate	Refrac- tive Index	Abbe's Number	Weather- ing Resist- ance	Appear- ance
Example 2	Trimethylol- propane 0.06 mol	(SCH ₂ CH ₂ CH ₂ NCO) ₂ 0.09 mol	1.56	45	0	Trans- parent
Example 3	" 0.06 mol	S(CH ₂ CH ₂ NCO) ₂ 0.09 mol	1.55	46	0	"
Example 4	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.04 mol	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	1.60	40	0	"
Example 5	" 0.04 mol	S(CH ₂ CH ₂ NCO) ₂ 0.08 mol	1.59	41	0	"
Example 6	C(CH ₂ OC(=O)CH ₂ SH) ₄ 0.04 mol	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	1.61	39	0	"
Example 7	"	S(CH ₂ CH ₂ CH ₂ NCO) ₂ 0.08 mol	1.59	42	0	"
Example 8	C(CH ₂ SCH ₂ CH ₂ SH) ₄ 0.04 mol	S(CH ₂ CH ₂ NCO) ₂ 0.08 mol	1.66	36	0	"

Table 1 (II)

	Active Hydrogen Compound	Polyisocyanate	Refractive Index	Abbe's Number	Weathering Resistance	Appearance
Example 9	$\text{S}(\text{CH}_2\text{CHCH}_2\text{SH})_2$ 0.04 mol	$\text{S}(\text{CH}_2\text{CH}_2\text{NCO})_2$ 0.08 mol	1.65	35	0	Transparent
Example 10	"	$(\text{SCH}_2\text{CH}_2\text{NCO})_2$ 0.08 mol	1.66	34	0	"
Example 11	$\text{C}(\text{CH}_2\text{SCH}_2\text{CH}_2\text{SH})_4$ 0.04 mol	$(\text{SCH}_2\text{CH}_2\text{NCO})_2$ 0.08 mol	1.67	34	0	"
Example 12	Trimethylolpropane 0.04 mol $\text{C}(\text{CH}_2\text{OC}(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{SH})_4$ 0.02 mol	$\text{S}(\text{CH}_2\text{CH}_2\text{NCO})_2$ 0.10 mol	1.57	43	0	"
Example 13	Ethylene glycol 0.02 mol $\text{C}(\text{CH}_2\text{SCH}_2\text{CH}_2\text{SH})_4$ 0.04 mol	" 0.10 mol	1.62	37	0	"
Example 14	$\text{C}(\text{CH}_2\text{OC}(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{SH})_4$ 0.02 mol $\text{S}(\text{CH}_2\text{CHCH}_2\text{SH})_2$ 0.02 mol	$(\text{SCH}_2\text{CH}_2\text{NCO})_2$ 0.08 mol	1.64	35	0	"

Table 1 (III)

	Active Hydrogen Compound	Polyisocyanate	Refractive Index	Abbe's Number	Weathering Resistance	Appearance
Example 15	Trimethylolpropane 0.04 mol Diethylene glycol 0.02 mol	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	1.57	45	0	Trans- parent
Example 16	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.02 mol C(CH ₂ OC(=O)CH ₂ SH) ₄ 0.02 mol	" 0.08 mol	1.61	40	0	"
Example 17	C(CH ₂ SCH ₂ CH ₂ SH) ₄ 0.02 mol S(CH ₂ CHCH ₂ SH) ₂ SH 0.02 mol	" 0.08 mol	1.66	35	0	"
Example 18	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.05 mol	S(CH ₂ CH ₂ NCO) ₂ 0.05 mol (SCH ₂ CH ₂ NCO) ₂ 0.05 mol	1.59	40	0	"

Table 1 (IV)


Comp. Ex.	Active Hydrogen Compound	Polyisocyanate	Refrac- tive Index	Abbe's Number	Weather- ing Resist- ance	Appear- ance
Comp. Ex. 1	1,4-Butanediol 0.07 mol	1,6-Hexamethylene diisocyanate 0.07 mol	1.50	55	0	"
Comp. Ex. 2	1,2,3-Trimercapto- benzene 0.033 mol	" 0.05 mol	1.66	27	0	"
Comp. Ex. 3	 0.05 mol	1,3-Xylylene diisocyanate 0.05 mol	1.61	27	Δ	slightly yellowed

Table 2 (I)

	Polyiso- cyanate	Active Hydrogen Compound	Internal Releas- ing Agent	Release Charac- teristics	Appear- ance	Refrac- tive Index	Abbe's Number
Exam- ple 20	Dithio- dipropyl diiso- cyanate 0.09 mol	Trimethylol- propane 0.06 mol	Unidain DS-403 200 ppm	0	High surface accuracy, Trans- parent	1.56	45
Exam- ple 21	Thiodiethyl diiso- cyanate 0.09 mol	"	F-Top EF-126 250 ppm	0	"	1.55	46
Exam- ple 22	"	"	Q2-120A 500 ppm	0	"	1.55	46
Exam- ple 23	Dithio- diethyl diiso- cyanate 0.09 mol	Diethylene glycol 0.09 mol	Triethyl- methyl- ammonium chloride 500 ppm	0	"	1.57	45
Exam- ple 24	"	Ethylene glycol 0.09 mol	Isopropyl acid phosphate 500 ppm	0	"	1.58	44

Table 2 (II)

	<u>Polyiso-</u> <u>cyanate</u>	<u>Active</u> <u>Hydrogen</u> <u>Compound</u>	<u>Internal</u> <u>Releas-</u> <u>ing Agent</u>	<u>Release</u> <u>Charac-</u> <u>teristics</u>	<u>Appear-</u> <u>ance</u>	<u>Refrac-</u> <u>tive</u> <u>Index</u>	<u>Abbe's</u> <u>Number</u>
Exam- ple 25	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.04 mol	Unidain DS-401 (Daikin) 100 ppm	0	High surface accuracy, Trans- parent	1.59	40
Exam- ple 26	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.04 mol	Q-2-120A (Dow) 150 ppm	0	"	1.61	39
Exam- ple 27	"	"	Trimethyl- acetyl- ammonium chloride 500 ppm	0	"	"	"
Exam- ple 28	"	"	Diiso- propyl acid phosphate 500 ppm	0	"	"	"
Exam- ple 29	S(CH ₂ CH ₂ CH ₂ NCO) ₂ 0.08 mol	"	Unidain DS-403 (Daikin) 100 ppm	0	"	1.59	42

Table 2 (III)

	Polyiso- cyanate	Active Hydrogen Compound	Internal Releas- ing Agent	Release Charac- teristics	Appear- ance	Refrac- tive Index	Abbe's Number
Exam- ple 30	(SCH ₂ CH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ OC(=O)CH ₂ SH) ₄ 0.04 mol	Unidain DS-401 (Daikin) 100 ppm Q2-120A (Dow) 100 ppm	0	High surface accuracy, Trans- parent	1.59	42
Exam- ple 31	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.04 mol	Dibutyl acid phosphate 500 ppm	0	"	1.59	39
Exam- ple 32	S(CH ₂ CH ₂ NCO) ₂ 0.08 mol	"	Trimethyl- octyl- ammonium chloride 500 ppm	0	"	1.58	41
Exam- ple 33	"	C(CH ₂ SCH ₂ CH ₂ SH) ₄ 0.04 mol	Unidain DS-401 (Daikin) 100 ppm	0	"	1.66	36

Table 2 (IV)

Exam- ple	Polyiso- cyanate	Active Hydrogen Compound	Internal Releas- ing Agent	Release Charac- teristics	Appear- ance	Refrac- tive Index	Abbe's Number
Exam- ple 34	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ SCH ₂ CH ₂ SH) ₄ 0.04 mol	Q2-120A (Dow) 150 ppm	0	High surface accuracy, Trans- parent	1.66	36
Exam- ple 35	"	"	Trimethyl- acetyl- ammonium chloride 500 ppm	0	"	"	"
Exam- ple 36	"	"	Diisopropyl acid phosphate 500 ppm	0	"	"	"
Exam- ple 37	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	"	Unidain DS-403 (Daikin) 100 ppm	0	"	1.67	34

Table 2 (V)

Example	Polyisocyanate	Active Hydrogen Compound	Internal Releasing Agent	Release Characteristics	Appearance	Refractive Index	Abbe's Number
Example 38	$(SCH_2CH_2NCO)_2$ 0.08 mol	$C(CH_2SCH_2CH_2SH)_4$ 0.04 mol	Unidain DS-401 (Daikin) 100 ppm Q2-120A (Dow) 100 ppm	0	High surface accuracy, Transparent	1.67	34
Example 39	"	$S(CH_2CHCH_2SH)_2$ SH 0.04 mol	Dibutyl acid phosphate 500 ppm	0	"	1.66	"
Example 40	$S(CH_2CH_2NCO)_2$ 0.08 mol	"	Trimethyl-octyl-ammonium chloride 500 ppm	0	"	1.65	35
Example 41	" 0.10 mol	Trimethylol propane 0.04 mol $C(CH_2OC(=O)CH_2CH_2SH)_4$ 0.02 mol	Unidain DS-403 200 ppm	0	"	1.57	43

Table 2 (VI)

Example	Polyisocyanate	Active Hydrogen Compound	Internal Releasing Agent	Release Characteristics	Appearance	Refractive Index	Abbe's Number
Example 42	$S(CH_2CH_2NCO)_2$ 0.10 mol	Ethylene glycol 0.02 mol $C(CH_2SCH_2CH_2SH)_4$ 0.04 mol	Dibutyl acid phosphate 500 ppm	0	High surface accuracy, Trans-parent	1.62	37
Example 43	$(SCH_2CH_2NCO)_2$ 0.08 mol	$C(CH_2OCCH_2CH_2SH)_4$ 0.02 mol $S(CH_2CHCH_2SH)_2$ SH 0.02 mol	Trimethyl octyl ammonium chloride 500 ppm	0	"	1.64	35
Example 44	"	Trimethylol propane 0.04 mol Diethylene glycol 0.02 mol	Q2-120A (Dow) 500 ppm	0	"	1.57	45

Table 2 (VII)

Exam- ple	Polyiso- cyanate	Active Hydrogen Compound	Internal Releas- ing Agent	Release Charac- teristics	Appear- ance	Refrac- tive Index	Abbe's Number
45	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.02 mol C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.02 mol	Diisopropyl acid phosphate 500 ppm	0	High surface accuracy, Trans- parent	1.61	40
46	"	C(CH ₂ SCH ₂ CH ₂ SH) ₄ 0.02 mol S(CH ₂ CHCH ₂ SH) ₂ SH 0.02 mol	"	0	"	1.66	35
47	S(CH ₂ CH ₂ NCO) ₂ 0.05 mol (SCH ₂ CH ₂ NCO) ₂ 0.05 mol	C(CH ₂ OC(=O)CH ₂ CH ₂ SH) ₄ 0.05 mol	"	0	"	1.59	40

Table 3 (I)

	<u>Polyiso-</u> <u>cyanate</u>	<u>Active</u> <u>Hydrogen</u> <u>Compound</u>	<u>Mold</u> <u>Treat-</u> <u>ment</u>	<u>Release</u> <u>Charac-</u> <u>teristics</u>	<u>Appear-</u> <u>ance</u>	<u>Refrac-</u> <u>tive</u> <u>Index</u>	<u>Abbe's</u> <u>Number</u>
Comp. Ex. 4	(SCH ₂ CH ₂ NCO) ₂ 0.09 mol	1,2,6-Hexane- triol 0.06 mol	No treat- ment	X	-	-	-
Comp. Ex. 5	"	"	External release treat- ment	O	Uneven surface, Trans- parent	1.57	44
Comp. Ex. 6	"	"	Reuse of external release treatment (mold used in Comp. Ex. 5)	X	-	-	-
Comp. Ex. 7	"	"	Use of PP mold	O	Bad surface accuracy, Trans- parent	1.57	44

Table 3 (II)

	<u>Polyiso-</u> <u>cyanate</u>	<u>Active</u> <u>Hydrogen</u> <u>Compound</u>	<u>Mold</u> <u>Treat-</u> <u>ment</u>	<u>Release</u> <u>Charac-</u> <u>teristics</u>	<u>Appear-</u> <u>ance</u>	<u>Refrac-</u> <u>tive</u> <u>Index</u>	<u>Abbe's</u> <u>Number</u>
Comp. Ex. 8	S(CH ₂ CH ₂ NCO) ₂ 0.09 mol	Trimethylol propane 0.06 mol	No treat- ment	X	-	-	-
Comp. Ex. 9	"	"	External release treat- ment	0	Uneven surface, Trans- parent	1.55	46
Comp. Ex. 10	"	"	Reuse of external release treatment (mold used in Comp. Ex. 9)	X	-	-	-
Comp. Ex. 11	"	"	Use of PP mold	0	Bad surface accuracy, Trans- parent	1.55	46

Table 3 (III)

	Polyiso- cyanate	Active Hydrogen Compound	Mold Treat- ment	Release Charac- teristics	Appear- ance	Refrac- tive Index	Abbe's Number
Comp. Ex. 12	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ OCCH ₂ SH) ₄ 0.04 mol	No treat- ment	X	-	-	-
Comp. Ex. 13	"	"	External release treat- ment	O	Uneven surface, Trans- parent	1.61	39
Comp. Ex. 14	"	"	Reuse of external release treatment (mold used in Comp. Ex. 13)	X	-	-	-
Comp. Ex. 15	"	"	Use of PP mold	O	Bad surface accuracy, Trans- parent	1.61	39

Table 3 (IV)

	Polyiso- cyanate	Active Hydrogen Compound	Mold Treat- ment	Release Charac- teristics	Appear- ance	Refrac- tive Index	Abbe's Number
Comp. Ex. 16	$S(CH_2CH_2CH_2NCO)_2$ 0.08 mol	$C(CH_2OC(=O)CH_2SH)_4$ 0.04 mol	No treat- ment	X	-	-	-
Comp. Ex. 17	"	"	External release treat- ment	O	Uneven surface, Trans- parent	1.59	42
Comp. Ex. 18	"	"	Reuse of external release treatment (mold used in Comp. Ex. 17)	X	-	-	-
Comp. Ex. 19	$(SCH_2CH_2NCO)_2$ 0.08 mol	$C(CH_2OC(=O)CH_2CH_2SH)_4$ 0.04 mol	Use of PP mold	O	Bad surface accuracy, Trans- parent	1.60	40

Table 3 (V)

<u>Polyiso-</u> <u>cyanate</u>	<u>Active</u> <u>Hydrogen</u> <u>Compound</u>	<u>Mold</u> <u>Treat-</u> <u>ment</u>	<u>Release</u> <u>Charac-</u> <u>teristics</u>	<u>Appear-</u> <u>ance</u>	<u>Refrac-</u> <u>tive</u> <u>Index</u>	<u>Abbe's</u> <u>Number</u>
Comp. Ex. 20	(SCH ₂ CH ₂ NCO) ₂ 0.08 mol	C(CH ₂ SCH ₂ CH ₂ SH) ₄ 0.04 mol	No treat- ment	-	-	-
Comp. Ex. 21	"	"	External release treat- ment	Uneven surface, Trans- parent	1.66	36
Comp. Ex. 22	"	"	Reuse of external release treatment (mold used in Comp. Ex. 21)	-	-	-
Comp. Ex. 23	"	"	Use of PP mold	Bad surface accuracy, Trans- parent	1.66	36

Table 3 (VI)

	<u>Polyiso-</u> <u>cyanate</u>	<u>Active</u> <u>Hydrogen</u> <u>Compound</u>	<u>Mold</u> <u>Treat-</u> <u>ment</u>	<u>Release</u> <u>Charac-</u> <u>teristics</u>	<u>Appear-</u> <u>ance</u>	<u>Refrac-</u> <u>tive</u> <u>Index</u>	<u>Abbe's</u> <u>Number</u>
Comp. Ex. 24	$S(CH_2CH_2NCO)_2$ 0.08 mol	$C(CH_2SCH_2CH_2SH)_4$ 0.04 mol	No treat- ment	X	-	-	-
Comp. Ex. 25	"	"	External release treat- ment	O	Uneven surface, Trans- parent	1.67	34
Comp. Ex. 26	"	"	Reuse of external release treatment (mold used in Comp. Ex. 25)	X	-	-	-
Comp. Ex. 27		$S(CH_2CHCH_2SH)_2$ _{SH} 0.04 mol	Use of PP mold	O	Bad surface accuracy, Trans- parent	1.66	34

Claims

- 5 1. A resin comprising the product of reacting one or more sulfur-containing aliphatic polyisocyanate compounds with one or more active hydrogen compounds selected from polyol compounds and polythiol compounds.
- 10 2. A process for producing a plastic lens comprising adding at least one internal mold releasing agent to a mixture of one or more of sulfur-containing aliphatic polyisocyanate compounds and one or more of active hydrogen compounds selected from polyol compounds and polythiol compounds followed by casting polymerization.
- 15 3. The resin of claim 1 or the process of claim 2 wherein the polythiol compounds are polythiol compounds having at least one sulfur atom in addition to the mercapto groups.
4. The resin of claim 1 or 3 or the process of claim 2 or 3 wherein the proportion of the sulfur-containing aliphatic polyisocyanate compound to the active hydrogen compound is a mole ratio of from about 0.5 to about 3.0 moles of functional isocyanate group per mole of functional (SH + OH) group.
- 20 5. The process of claim 2,3 or 4 wherein the internal mold releasing agent is a fluorine containing nonionic surface active agent.
6. The process of claim 2,3 or 4 wherein the internal mold releasing agent is a silicon containing nonionic surface active agent.
- 25 7. The process of claim 2,3 or 4 wherein the internal mold releasing agent is an alkyl quaternary ammonium salt.
8. The process of claim 2,3 or 4 wherein the internal mold releasing agent is an acidic phosphate.
9. The process of any of claims 2-8 wherein the internal mold releasing agent is present in an amount of from about 0.1 to about 10,000 ppm per sum of the sulfur-containing aliphatic polyisocyanate compound and the active hydrogen compound.
- 30 10. The process of any of claims 2-9 wherein the casting polymerization is carried out at a temperature of from about -20°C to about 200°C.
11. A plastic lens comprising the resin of any of claims 1,3 and 4 and/or as produced by a process according to any of claims 2-10.

12

EUROPEAN PATENT APPLICATION

21 Application number: 89301397.9

51 Int. Cl.⁴: **C 08 G 18/77**
C 08 G 18/38

22 Date of filing: 15.02.89

30 Priority: 17.02.88 JP 32842/88
18.02.88 JP 33871/88
18.02.88 JP 33872/88
22.02.88 JP 37515/88
22.02.88 JP 37523/88
22.02.88 JP 37525/88

43 Date of publication of application:
23.08.89 Bulletin 89/34

84 Designated Contracting States:
CH DE FR GB IT LI NL

88 Date of deferred publication of search report:
21.03.90 Bulletin 90/12

71 Applicant: **MITSUI TOATSU CHEMICALS,**
INCORPORATED
2-5, 3-chome, Kasumigaseki
Chiyoda-ku Tokyo (JP)

72 Inventor: **Nagata, Teruyuki**
154, Shiraganemachi
Omatu-shi Fukuoka-ken (JP)

Okazaki, Koju
35, Yamashitamachi
Omatu-shi Fukuoka-ken (JP)

Kajimoto, Nobuyuki
4-1413-1315, Shiomidai 1-chome Isogo-ku
Yokohama-shi Kanagawa-ken (JP)

Miura, Tohru
1612-1-26, Kosugayacho Sakae-ku
Yokohama-shi Kanagawa-ken (JP)

Kanemura, Yoshinobu
2882, Iijimacho Sakae-ku
Yokohama-shi Kanagawa-ken (JP)

Sasagawa, Katsuyoshi
1510-1-411, Shinyoshidacho Kohoku-ku
Yokohama-shi Kanagawa-ken (JP)

74 Representative: **Stuart, Ian Alexander et al**
MEWBURN ELLIS & CO. 2/3 Cursitor Street
London EC4A 1BQ (GB)

54 Resin for plastics lens, and method for its preparation.

57 The present invention relates to resin useful in preparing plastic lenses having a high refractive index comprising reacting an aliphatic polyisocyanate compounds having at least one sulfur atom with one or more of active hydrogen compounds selected from the group consisting of a polyol, a polythiol having sulfur atoms only in a mercapto groups, and a polythiol having at least one sulfur atom other than in the mercapto groups: lenses containing the above mentioned resin: and a method for the preparation thereof characterized by adding an internal release agent to the mixture of the above-mentioned raw materials in casting lenses from the resin and lenses obtained by this method.

EP 0 329 387 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 30 1397

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
X	DE-A-1 045 641 (BAYER) * Column 1, line 43 - column 3, line 16; claim *	1	C 08 G 18/77 C 08 G 18/38
P,A	EP-A-0 271 839 (MITSUI TOATSU) * Column 2, line 49 - column 5, line 1; claims 1-3 *	1-11	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			C 08 G G 02 B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19-12-1989	Examiner BOURGONJE A.F.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03.82 (P0401)